



STRONGCRETE

PAVE-SET

**PAVE-SET is a jointing material specially formulated to allow rapid filling of vertical joints between segmented clay and masonry pavers.
For use on flexible pavements only.**

SAFETY ADVICE SKIN/EYE IRRITATION

- Avoid contact with the skin by wearing suitable gloves and clothing.
- In the event of contact, wash skin immediately with clean water to help minimize possible irritation.
- If any material gets into the eyes, wash immediately and repeatedly with eye wash solution or clean water.
- If irritation persists, seek medical advice.

RESPIRATORY IRRITATION

- This material may contain a quantity of crystalline silica and suitable respiratory equipment should be used when handling.

STRONGCRETE PAVE-SET has been specially formulated using graded, washed sand and additives to allow rapid filling of all vertical joints in segmental paving.

STRONGCRETE PAVE-SET is a jointing material which generally conforms to guidelines for jointing material set out by the Clay Brick and Paver Institute's 'Design Manual One' for Segmental Paving Units.

PAVE-SET IS SUITABLE FOR USE IN THE FOLLOWING AREAS:

1. Driveways
2. Footpaths
3. Where there is heavy traffic movement
4. Where mobile vacuum sweepers are used
5. Sloping sites
6. In high wind areas
7. Roadways/Airport Standing areas (Where Designed)

PAVE-SET MUST BE USED IN ACCORDANCE WITH THE FOLLOWING DIRECTIONS:

STRONGCRETE PAVE-SET must be spread onto dry pavers and swept into all vertical joints until completely filled. The paved area must then be swept clean of **STRONGCRETE PAVE-SET** and receive at least two passes of a plate vibrator to ensure compaction of tight joints. A rubber roller attachment or carpet can be used under the plate to protect the paver from damage. Check with the paving supplier as to the suitability of compacting pavers 50mm or less in thickness.

The joints should then be topped up by sweeping more **STRONGCRETE PAVE-SET** over the area prior to a final compaction consisting of at least two more passes of the plate vibrator.

Before applying an even spray of clean water over the pavement, you must ensure that all excess **STRONGCRETE PAVE-SET** is swept clean from the surface of the pavers to avoid **STRONGCRETE PAVE-SET** adhering to the surface.

Thorough gradual soaking of the **STRONGCRETE PAVE-SET** area should be completed to allow water to penetrate through the jointing material.

Suggest a small area (1m) be conducted to ascertain paver suitability (moisture and surface texture) prior to full application.

STRONGCRETE PAVE-SET, once dried will remain flexible and allow slight movement of pavers without cracking. Your paved area will be ready for use after a minimum of 24 hours setting time.

- DO NOT USE ON RUSTIC NON SMOOTH CLAY PAVERS AS STAINING AND SCUFFING MAY OCCUR.
- AVOID CLEANING PAVERS WITH A HIGH PRESSURE WATER CLEANER.
- NOT RECOMMENDED FOR PAVERS LAID DIRECTLY ON CONCRETE.
- USE QUALITY BEDDING SAND I.E. COURSE WASHED RIVER SAND.
- AVOID FLOODING OF PAVED AREAS.

PLEASE NOTE: Avoid applying to wet or damp surfaces as **STRONGCRETE PAVE-SET** will begin to 'gel' and restrict the flow of material into the joints. If complications occur, **STRONGCRETE PAVE-SET** can be scrubbed from the paver surface by using a stiff brush. Minimal maintenance may be required in certain areas. **STRONGCRETE PAVE-SET** will help retard weed growth and insect infestation. The contents of this bag will cover approx. 9-10m² at 3mm maximum gap width. This will depend upon the shape and size of the paver. Do not allow vehicular traffic over surface for 24 hours.



**FIORINI
RAINSHIELD**
WWW.FIORINI.BIZ
TEL +39 071 66061



PROUDLY MANUFACTURED IN NEW ZEALAND BY STRONGCRETE LTD
PO Box 109, Greenhithe, Auckland 0756
Ph 0800 MYSTRONGCRETE (697876) | Order Fax 0800 379 329
sales@strongcrete.co.nz | www.strongcrete.co.nz

www.strongcrete.co.nz